

JS Products Inc

Chemical test rating for Nitrile Gloves
VG= Very Good, G= Good, F=Fair, P=Poor

Chemical	Nitrile
Acetaldehyde*	G
Acetic acid	VG
Acetone*	P
Ammonium hydroxide	VG
Amy acetate*	P
Aniline	P
Benzaldehyde*	G
Benzene*	F
Butyl acetate	P
Butyl alcohol	VG
Carbon disulfide	F
Carbon tetrachloride*	G
Castor oil	VG
Chlorobenzene*	P
Chloroform*	F
Chloronaphthalene	F
Chromic acid (50%)	F
Citric acid (10%)	VG
Cyclohexanol	VG
Dibutyl phthalate*	G
Diesel fuel	VG
Diisobutyl ketone	P
Dimethylformamide	G
Diocetyl phthalate	VG
Dioxane	G
Epoxy resins dry	VG
Ethyl acetate*	F
Ethyl alcohol	VG
Ethyl ether*	G
Ethylene dichloride*	P
Ethylene glycol	VG
Formaldehyde	VG
Formic acid	VG
Freon 11	G
Freon 12	G
Freon 21	G
Freon 22	G
Furfural*	G
Gasoline- leaded	VG
Gasoline- unleaded	VG

Glycerin	VG
Hexane	G
Hydrazine (65%)	G
Hydrochloric acid	G
Hydrofluoric acid (48%)	G
Hydrogen peroxide (30%)	G
Hydroquinone	F
Isooctane	VG
Kerosene	VG
Ketones	P
Lacquer thinners	P
Lactic acid (85%)	VG
Lauric acid (36%)	VG
Lineolic acid	G
Linseed oil	VG
Maleic acid	VG
Methyl alcohol	VG
Methylamine	G
Methyl bromide	F
Methyl chloride*	P
Methylethylketone*	P
Methylisobutylketone*	P
Methylmethacrylate	F
Monoethanolamine	VG
Morpholine	G
Naphthalene	G
Napthasaliphatic	VG
Napthasaromatic	G
Nitricacid*	F
Nitricacidredandwhitefuming	P
Nitromethane(95.5%)*	F
Nitropropane(95.5%)	F
Octylalcohol	VG
Oleicacid	VG
Oxalicacid	VG
Palmiticacid	VG
Perchloricacid(60%)	G
Perchloroethylene	G
Petroleumdistillates(naphtha)	VG
Phenol	F
Phosphoricacid	VG
Potassiumhydroxide	VG
Propylacetate	F
Propylalcohol	VG
Propylalcohol(iso)	VG
Sodiumhydroxide	VG
Styrene	F

Styrene(100%)	F
Sulfuricacid	G
Tannicacid(65)	VG
Tetrahydrofuran	F
Toluene*	F
Toluenediisocyanate(TDI)	F
Trichloroethylene*	G
Triethanolamine (85%)	VG
Tung oil	VG
Turpentine	VG
Xylene*	F